



Höpke Möbelstoff-Handels GmbH
Simonsgasse 19-21
96489 Niederfüllbach
Germany

Your notice of
03-10-2019

Your reference

Date
18-05-2020

Analysis Report 19.05608.05

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - smouldering cigarette test**
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - Match flame equivalent**

Identification number	Information given by the client	Date of receipt
T1921358	Melia FR	03-10-2019



Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T1921358 - Melia FR

IMO upholstered furniture

Information given by the client

Type of furniture	Upholstery
Fabric	
Composition	100% polyester FR
Structure	Plain / weave
Number of threads - warp	24/cm
Number of threads - weft	32.3/cm
Yarn count - warp	334 dtex
Yarn count - weft	167 dtex
Thickness in mm	
Weight g/m ²	325
Colour	15207 café
Inherently FR treated	yes



Reference: T1921358 - Melia FR

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test	30-10-2019
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - $\pm 36 \text{ kg/m}^3$


Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$


Mass: $(0.95 \pm 0.15) \text{ mm}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Pass



Reference: T1921358 - Melia FR

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test 30-10-2019
 Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
 Deviation from the standard -
 Conditioning 23°C, relative humidity 50%

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Filling SB 36140 (Recticel) - fire retardant foam - \pm 36 kg/m³

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
	non-ignition	non-ignition

Conclusion Pass