



Date: 13/06/2024

TEST REPORT

FIRE TEST

Baaiensstraat 11, B-9240 Zele, Tel: +32(0)52/45 85 40 Fax: +32(0)52/45 85 45

Customer		CTF2000	
Company	HÖPKE TEXTILES	Made by	Aylin Kiran
Compound	FLAMAWAY CRIB 5	Function	Lab Project Coordinator
Description of the assembly			
Article indicated: AMILIO			
Total fabric weight: 588 g/m²			
The fabric has been water soaked in accordance with BS 5651			
FR test method for upholstered seating			
BS 5852 : 2006 - Crib V test			
Type of foam used for testing : CMHR35 (*)			
		Test results	PASS Criteria
Flaming criteria			
Unsafe escalating combustion		No	No
Test assembly consumed		No	No
Flames to extremities		No	No
Flame through thickness		No	No
Flame time (min)		4'35"	< 10 min
Smouldering criteria			
Unsafe escalating combustion		No	No
Test assembly consumed		No	No
Smoulders to extremities		No	No
Smoulders through thickness		No	No
Smouldering time (min)		Na	< 60 min
Conclusion			
The sample meets the requirements for BS 5852- source 5.			

(*) Type of foam used for testing : CMHR35 : combustion modified high resilience foam 35kg/m³

Note:

CTF 2000 - lab is not a accredited test laboratory for fire resistant testing . The test results can be used as a guidance but not for official use . The information submitted in this report is based on our current knowledge and experience.
We don't have for all FR tests the official installation as described in the standard, but for a number of tests, we imitate the test as close as possible . This data does not imply any legally binding assurance of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed