

Date: 16/07/2020

OTECON

## TEST REPORT FIRE TEST

Baaikensstraat 11, B-9240 Zele, Tel: +32(0)52/45 85 40 Fax: +32(0)52/45 85 45

Customer		CTF2000			
Company	Höpke Textiles	Made by	Aylin Kiran		
Compound	Flamaway finish	Function	Lab Technician		
Description of the assembly					
Article indicated: VERANO FR					
Total fabric weight: 573 g/m <sup>2</sup>					
The fabric has been water soaked in accordance with BS 5651					
FR test method for upholstered seatings BS 5852 : part 1 : 1979 , source 0 - smouldering cigarette					
	of foams used for testing: RP21/140 (*)				
		<u>Test results</u>		PASS Criteria	
Flaming ?		No		No	
Time for all heat, smoke, glowing to stop (min)		< 60 min		< 60 min	
Final examination :					
- internal smouldering ?		No		No	
- charing more than 100 mm in any direction?		No		No	
• •	cause it is unsafe to continue	No		No	
Conclusion					
The sample meets the requirements for BS 5852- source 0.					
FR test method for upholstered seatings					
BS 5852 : part 1 : 1979 , source 1 - butane gas flame					
Type of foams used for testing: RP21/140 (*)					
Flame application time	e : 20 sec	T	T+0	DACC Critorio	
Afterflaming time (sec	,	<u>Test 1</u> 3"	<u>Test 2</u> 11"	PASS Criteria < 2 min	
	ke, glowing to stop (min)	<15min	<15min	< 15 min	
Flames into the foam	· · · · · · · · · · · · · · · · · · ·	No	No	No	
Final examination :			110	140	
- internal smouldering	?	No	No	No	
Ü	ecimen are reached or the	No	No	No	
	specimen is destroyed?				
	cause it is unsafe to continue	No	No	No	
Conclusion					
The sample meets the requirements for BS 5852- source 1.					

(\*) Type of foams used for testing : -RP21/140 : polyurethane foam 20 – 22 kg/m³ -CMHR35 : combustion modified high resilience foam 35kg/m³

## Note.

CTF 2000 - lab is not a accredited test laboratory for fire resistant testing . The test results can be used as a guidance but not for official use . The information submitted in this report is based on our current knowledge and experience.

We don't have for all FR tests the official installation as described in the standard, but for a number of tests, we imitate the test as closely as possible. This data does not imply any legally binding assurance of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed